



510 Ninth Avenue, Beaver Falls, PA 15010

Telephone: 724 843 8300

Fax: 724 843 5644

Email: sales@mcdanelceramics.com

Web: www.mcdanelceramics.com

## AP35 99% ALUMINA

TYPE C799 TO IEC 60672

### Composition

Alumina	Al <sub>2</sub> O <sub>3</sub>	99.0%
Silica	SiO <sub>2</sub>	0.7%
Magnesia	MgO	0.07%
Iron Oxide	Fe <sub>2</sub> O <sub>3</sub>	0.07%
Sodium Oxide	Na <sub>2</sub> O	0.05%
Calcia	CaO	0.03%

### Physical Properties

Bulk Density	Open Porosity	Flexural Strength		Compressive Strength
		20°C	1000°C	20°C
3.83 g/cm <sup>3</sup>	0%	345 Mpa	145 Mpa	2550 Mpa
239 lbs/ft <sup>3</sup>	0%	50 ksi	30 ksi	370 ksi

### Thermal Properties

Conductivity		Expansion Coefficient	Max Use Temperature (no load)
20°C	800°C		
29 W/m <sup>°K</sup>	7.2 W/m <sup>°K</sup>	8.4 x 10 <sup>-6</sup> /C°	1700°C
201 BTU.in/ft <sup>2</sup> .hr°F	50 BTU.in/ft <sup>2</sup> .hr°F	4.7 x 10 <sup>-6</sup> /F°	3092°F

These values represent typical properties of standard materials.

Values should be used only for comparison and should not be used as a warranty.