

510 Ninth Avenue, Beaver Falls, PA 15010

Telephone: 724 843 8300

Fax: 724 843 5644

Email: sales@mcdanelceramics.com

Web: www.mcdanelceramics.com

MV30 MULLITE

TYPE C610 TO IEC 60672

Composition

Alumina	Al ₂ O ₃	60.0%
Silica	SiO ₂	37.9%
Iron Oxide	Fe ₂ O ₃	0.5%
Potassium Oxide	K ₂ O	0.6%
Titania	TiO ₂	0.5%
Sodium Oxide	Na ₂ O	0.2%
Calcia	CaO	0.1%
Magnesia	MgO	0.2%

Physical Properties

Bulk Density	Open Porosity	Flexural Strength	Compressive Strength
		20°C	20°C
2.75 g/cm ³	0%	180 Mpa	1310 Mpa
172 lbs/ft ³	0%	26 ksi	190 ksi

Thermal Properties

Conductivity		Expansion Coefficient	Max Use Temperature (no load)
20°C	800°C		
3.6 W/m ^{°K}	2.6 W/m ^{°K}	5.0x 10 ⁻⁶ /C°	1500°C
25 BTU.in/ft ² .hr°F	18 BTU.in/ft ² .hr°F	2.8 x 10 ⁻⁶ /F°	2732°F

Electrical Properties

Volume Resistivity	
20°C	600°C
>10 ¹³ Ω.cm	1.5x10 ⁷ Ω.cm

These values are typical but significant differences may occur depending on geometry,

510 Ninth Avenue, Beaver Falls, PA 15010

mass, specific processing methods used, and the surface finish of final components.